

Data Sheet

MILD STEEL LIGHT PLATE G250

NZ STANDARD

- AS/NZS 1594:2002
- AS/NZS 1365:1996

INTERNATIONAL STANDARDS

- JISG 3101– SS400
- ASTM A 1011 SS Grade 40
- EN 10025-2-S235JR
- DIN 17100 St44-2

PRODUCT DESCRIPTION

Hot rolled structural product with yield strength of 250MPa, good ductility and good weldability.

SUPPLY CONDITIONS

- Thickness Range 1.6mm—12mm
- Tolerances AS1365 or equivalent
- Flatness Class A

TYPICAL USES

- Structural members
- Roll forming applications
- Press brake forming applications
- General fabrication

Data sheet

MILD STEEL LIGHT PLATE G250

CHEMICAL COMPOSITION				
Element	Guaranteed Maximum	Typical %/ Thickness (mm)		
		2<t < 2.5	2.5<t < 6.0	6.0<t < 12.0
Carbon	0.20	0.05	0.075	0.170
Silicon	0.03	0.007	0.008	0.008
Manganese	1.20	0.60	0.60	0.60
Phosphorus	0.040	0.014	0.016	0.016
Sulphur	0.030	0.018	0.018	0.018

MECHANICAL PROPERTIES				
Typical Properties (Transverse)		Thickness Range (mm)		
		2<t<3.0	3.0<t<6.0	6.0<t<12
Guaranteed Min.	Yield Strength (MPa)	250	250	250
	Tensile Strength (MPa)	350	350	350
Typical	Yield Strength (MPa)	280	300	290
	Tensile Strength (MPa)	390	410	450

FABRICATING PERFORMANCE	
1 = Limited 5 = Excellent	
METHOD	RATING
Drawing	2
Pressing	3
Bending	4
Roll forming	4
Welding	5

The information contained in this data sheet is provided by the way of general information only, and should not be relied upon by any person. LaserTek Profiles Ltd take no responsibility for any adverse consequences of any nature which arise as a result of reliance on this datasheet. Please refer to our office for specific information